## MAPPA BURL / POPLAR BURL

Common Name(s): Black Poplar, Lombardy Poplar Scientific Name: Populus nigra Distribution: Europe, western Asia, Northern Africa; planted as an ornamental in North America Tree Size: 65-100 ft (20-30 m) tall, 3-5 ft (1-1.5 m) trunk diameter Average Dried Weight: 24 lbs/ft<sup>3</sup> (385 kg/m<sup>3</sup>) Specific Gravity (Basic, 12% MC): .31, .39 Janka Hardness: 460 lb<sub>f</sub> (2,020 N) Modulus of Rupture: 9,230 lb<sub>f</sub>/in<sup>2</sup> (63.7 MPa) Elastic Modulus: 1,045,000 lb<sub>f</sub>/in<sup>2</sup> (7.21 GPa) Crushing Strength: 5,220 lb<sub>f</sub>/in<sup>2</sup> (36.0 MPa) Shrinkage: Radial: 4.0%, Tangential: 9.3%, Volumetric: 12.3%, T/R Ratio: 2.3

**Color/Appearance:** Heartwood tends to be a light brown. Sapwood is a pale yellow to nearly white, and isn't clearly demarcated, tending to gradually blend into the heartwood. This species also yields a unique burl that's commonly sold as Mappa or Mapa.

<u>Grain/Texture:</u> Grain is generally straight to slightly irregular or interlocked. Uniform medium texture with low natural luster.

